



STRONGWALL INDUSTRIES, INC.

STRONGCOTE SC-111

Pedestrian Grade Traffic Deck Membrane System Product Data Sheet

Product Description

SC-111 is a breathable coating system. It can be installed in both interior and exterior pedestrian traffic areas. It is suitable for all masonry surfaces including cast in place and precast concrete. This two-part system is comprised of a liquid latex polymer containing migratory corrosion inhibitors and special anti-slip aggregate for skid resistance. Since the non-skid aggregate is contained in the mix, there is no need for sand broadcasting common with most traffic membranes. Furthermore, inclusion of the aggregate provides a more uniform wearing surface and longevity to the coating system.

Yield and Packaging

5-gallons of liquid packaged in a 6-gallon pail and two 55lbs bags of powder form one unit.

Unit yield: 600 sq. ft at 25 mils

Note: Minimum two coat required for the system

Shelf Life

One year.

Storage Conditions

Indoors, in a dry location, at temperatures not exceeding 90° F or lower than 35 ° F

Typical Physical Properties at 75°F (24°C)

Adhesion ASTM C-882, Type 1	515 psi
Static Coefficient of Friction ASTM C 1028.....	(Dry) 0.89
	(Wet) 0.60
Flammable Properties ASTM E84	Flame spread - 4
	Smoke Density - 0
Fire Resistance UL 790	Complies as Class A
Freeze-Thaw Resistance - 50 Cycles ...no scaling/peeling/flaking	
(Concrete cylinders immersed for 8 hrs in coated salt water solution followed by 16 hrs of freezing)	
Water Absorption Weight gain of 4" coated concrete cube after 21 days water immersion (CMCH)	<2%
Water Vapor Permeability ASTM E96	99.7 grams/sq. meter/24 hrs. or 14.3 perms
Weathering ASTM G23	No visible degradation
(Method1/Procedure; 60 cycles)	

Where to use

SC-111 should be applied as a protection system for concrete structures such as balconies, pools, decks, train passenger platforms, stadium walkways and aisles, water storage tank covers, highway median dividers, and noise barriers.

Advantages

1. Low water permeability that mask against water and salt penetration
2. High water vapor transmission that eliminates freeze/thaw damage.
3. Breathability allows for slab on grade, split slab and metal pan applications.
4. Contains migratory corrosion inhibitors that suppress rebar corrosion.
5. Provides excellent traction in both wet and dry conditions
6. Non-flammable, Class A, zero VOC, non toxic and odorless
7. Excellent UV resistance.
8. LEED (Leadership in Energy and Environmental Design.) Credit Points may be available under 5 different Classifications.
9. Does not contain chemicals targeted by Green Seal Standard GS-11 and LEED-CS as unacceptable.

Overview of Application Procedures

Crack Treatment Component

EM-100-N, a rubber emulsion, packaged in 5-gallon pails.

Mixing Ratio: Apply directly from pail

Yield: 800 lineal ft at 50 mils wet at 2" wide per 5-gal pail

Traffic-bearing Component

Strongcote #3 Liquid, a latex vinyl copolymer, 5 gallons of liquid packaged in a 6-gallon pail and Strongcote #3 Powder, an aggregate catalyst, packaged in 55-pound bags includes migratory corrosion inhibitors.

Mixing Ratio: Two 55-lb bags of Strongcote #3 Powder and one 5-gallon pail of Strongcote #3 Liquid form one unit.

Average Yield Per Unit: 600 sq. ft. @ 25 mils

This is always a two (2) 25mils coat system.

Optional Color Topping Component

Apply to improve cleanability and to enhance color quality

Resicolor #4 or Resiclear #6 homopolymer toppings, packaged in 5-gallon pails.

Mixing Ratio: Apply directly from pail.

Yield: 1000-1200 sq. ft. per 5-gallon pail

Mixing: Stir for 30 seconds.

Application: Apply on a clean, dry surface, using a short nap roller.

SKID RESISTANCE and CLEANABILITY

In general the more aggressive the finished surface the greater the coefficient of friction and corresponding skid resistance, the more difficult to clean. The smoother the finished texture the easier the surface is to clean, but there is a loss of skid resistant properties.

CHEMICAL RESISTANCE

See SWI Products Corp's., Chemical Resistance Guidelines for chemical resistance of a product or system, as well as the types of test performed:

- ASTM C868 Standard Test Method for Chemical Resistance of Protective Lining.
- ASTM C267 Standard Test Method for Chemical Resistance of Mortars, Grouts, and Monolithic Surfacing and Polymer Concretes.
- ASTM D1308 Standard Test Method for Effect of Household Chemicals on Clear and Pigmented Organic Finishes
- Strongwall Industries Inc. Proprietary Testing

Note: Chemical resistance is a functional test, usually limited to changes in weight or thickness measured in loss or gain and does not evaluate subject aesthetic issues. To determine aesthetic issues, SWI recommends testing the products or system in accordance with intended end use.

Cleaning

Cleaning and disinfecting compounds and cleaning techniques can affect the color, gloss, texture and performance of the system. As a precautionary step, SWI recommends that the end-user test their cleaning and disinfecting compounds on a sample or on a small, out of the way finished area, utilizing the intended cleaning technique prior to cleaning the entire surface area. If no deleterious effects are observed, the procedure can be continued. If the cleaning and disinfecting compounds or cleaning techniques damage the system, modification of the cleaning material or techniques will be required. Contact your Representative for additional information.

Cleaning Tools

Clean all tools with water immediately after use. If cured, mechanical means will be necessary.

First Aid

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with plenty of water for at least 15 minutes. For respiratory problems, remove person to fresh air. Contact a physician. Keep container tightly closed. Keep out of reach of children, Not for internal consumption. For industrial use only.

Specification Assistance

Consult Strongwall Industries Incorporated for specification assistance and details. This consultation is highly recommended prior to specification.

Testing

The technical data contained herein is the result of tests made in manufacturer's laboratories or in independent laboratories using small scale equipment, following generally accepted trade practices. Although this information is believed to be true and accurate, the use of different equipment for testing under dissimilar conditions or the testing of samples produced under dissimilar conditions may develop substantially different results.

Strongwall Industries, Inc. 107 Chestnut Street, Ridgewood, NJ 07450 Phone: (201) 445-4633 Fax (201) 447-2317
Email: info@strongwall.com Website: www.strongwall.com

All information provided by Strongwall Industries concerning Strongwall products, including but not limited to, any recommendations and advice relating to the application and use of Strongwall products, is given in good faith based on Strongwall's current experience and knowledge of its product when properly stored, handled, and applied under normal conditions in accordance with Strongwall's instructions. In practice, the differences in materials, substrates, storage and handling conditions, actual sight conditions and other factors outside of Strongwall's control as such that Strongwall assumes no liability for the provision of such information, advice, recommendations, or instructions related to its products, nor shall any legal relationship be created by or arise from the provision of such information, advice, recommendations, or instructions related to its products. The user of the Strongwall product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with the full application of the product(s). Strongwall reserves the right to change the properties of its products without notice. All sales of Strongwall product(s) are subject to its current terms and conditions of sale which are available by calling 201-445-4633.

Prior to each use of any Strongwall product, the user must always read and follow the instructions on the product's most current Product Data Sheet, product label, and Material Safety Data Sheet which are available by calling at 201-445-4633. Nothing contained in Strongwall materials relieves the user of the obligation to read and follow the instructions for each Strongwall product as set forth in the current Product Data Sheet application instructions, product label, and Material Safety Data Sheet prior to product use.

MATERIAL GUARANTEE

Strongwall Industries, Inc. (hereafter referred to as Strongwall) guarantees materials only for a period of 1 year from the date of installation, when applied to an approved substrate by an approved applicator in accordance with Strongwall's written specifications, application instructions, and Product Data Sheet. **STRONGWALL DISCLAIMS ANY OTHER GUARANTEE OR WARRANTY EXPRESS OR IMPLIED OF THE MATERIALS AND THIS GUARANTEE SHALL BE THE SOLE REMEDY OF ANY PERSON WHO PURCHASES OR USES THE MATERIALS.**

This guarantee applies only to material defects and will not apply in instances where failure has been caused by substrate defects including improper preparation, structural movement or settlement. In addition, it will not cover vandalism, accidents, acts of God, ordinary wear or any other damage not associated with normal usage. Where the materials have been applied over a previous coated surface, guarantee is limited to adhesion of the materials to previous coating and does not guarantee adhesion of previous coating to substrate.

This guarantee is valid only upon completion of the job, proper maintenance of all systems, payment in full to Strongwall and after the applicator and owner have affixed their signatures to the fully executed document to signify their acceptance of its terms and conditions and to release Strongwall of all claims and obligations other than those set forth in the above paragraph. A fully executed copy must be returned to Strongwall.

In the event of any kind of failure, the owner will advise the approved applicator in writing. The applicator will make an inspection to determine the cause of such failure. Should materials failure occur, Strongwall will provide replacement of materials that may be required to correct deficiencies. There are no express agreements other than those set forth in the above paragraphs.

Buyer understands and agrees that any and all warranties implied by the provisions of the Uniform Commercial Code are executed from this sale.